

Technical Data Sheet

Interflon Fin Super Dry Lube

Universal dry film lubricant with MicPol® technology

Multipurpose penetrating dry long-lasting lubricant for a variety of indoor and outdoor applications. Repels water, dust, sand and other contaminants. Removes and prevents rust.

Cleans, lubricates and protects (CLP). Goes on wet, cleanses, displaces moisture, breaks down deposits and penetrates even into the most inaccessible areas. Loosens seized, rusted and frozen parts and prevents the formation of rust and other corrosives. Holds up to high pressures, resists water wash-off and will not attract dirt, dust and other abrasives.

Applications

Where parts are exposed to contamination or moisture, they need to be coated to prevent rust and corrosion; providing protection where conventional lubricants fail. Excellent choice for the lubrication of chains, cables, sliding tracks, (air) tools, joints, cams, belts, saws, guides, springs, pulleys, threaded parts, bolts, rollers, taps, pins, bushings, valves, conveyors and many other applications.

Advantages

- ⦿ Reduction of wear
- ⦿ Contains no propellant, 100% product
- ⦿ Small, practical packaging for easy handling
- ⦿ Clean and dry lubricant, does not drip
- ⦿ Longer lasting
- ⦿ Replaces many other products
- ⦿ Water resistant
- ⦿ Frees sticking parts
- ⦿ Cleans and protects against corrosion
- ⦿ Dirt does not stick to the dry film
- ⦿ Stable lubricating film with MicPol®
- ⦿ No stick slip
- ⦿ PFAS free

Instructions for use

Shake or stir before use. Parts should be cleaned first with a solvent or alkaline cleaning agent. Spray Interflon Fin Super Dry Lube onto parts and allow to penetrate. Wipe off the excess of lubricant with a clean cloth.

Note: do not use too much Interflon Fin Super Dry Lube. Applying a thin layer, with occasional re-lubrication, gives a better result than a thick layer.

Property	Result	Method
Composition	Mixture of mineral and vegetable oils, additives and Micpol®	
Colour	Yellowish brown	
Odour	Like oil	
Density 20°C	0.84 g/cm ³	
Kinematic viscosity 40°C	23 cSt	ASTM D445
Lowest application temperature	-43°C	
Highest application temperature**	170°C	
Biodegradability	53%	ASTM D7373-07
Manufacturing date	The batch number consists of a 8-digit number. The first 4 numbers represent the YY/MM of the manufacturing.	
Shelf life*	4 years	
Conductivity	>2000 pS/m	ASTM D2624
Dielectric strength	128 kV/cm	IEC 60156

* Shelf life of the product in original and unopened packaging. Storage temperatures <0°C need to be avoided to guarantee product quality. ** High temperature limit is valid after evaporation of solvent.

This information is based on our best and present knowledge and intended to provide general notes about the product and intended use. Therefore it shouldn't be construed as guaranteeing properties of the product described or suitability for an application. Any existing industrial property rights must be observed. Quality of our products is guaranteed under our General Conditions of Sale. Interflon® and MicPol® are registered trademarks of Interflon BV. Typical properties mentioned in this document are based on our production tolerances and do not represent a specification. Variations that do not affect product performance are to be expected during normal manufacturing. Information provided in this document is subject to change without notice in advance.