

SKF High load, wide temperature bearing grease

LGWM 2

SKF LGWM 2 is a synthetic-mineral oil based grease using the latest complex calcium sulphonate thickener technology. It is suitable for applications subjected to high loads, wet environments and fluctuating temperatures.

- Excellent corrosion protection
- · Excellent mechanical stability
- Excellent high load lubricating capacity
- Good false brinelling protection
- Good pumpability down to low temperatures

Typical applications

- · Wind turbine mains shafts
- Heavy duty off road applications
- Snow exposed applications
- Marine and offshore applications
- Spherical roller thrust bearing applications








Packsize	Designation	Packsize	Designation
20 ml cartridge	LGWM 2/0.4	Electro-mechanical lubricators	
kg can	LGWM 2/5	TLSD series 125 ml refill	LGWM 2/SD125
l8 kg pail	LGWM 2/18	TLSD series 250 ml refill	LGWM 2/SD250
60 kg drum	LGWM 2/50	Electro-mechanical lubricant dispensers	\sqrt{1} LGW
l80 kg drum	LGWM 2/180	TLMR 101 series 380 ml refill (incl. battery)	LGWM 2/MR380B
Sas driven lubricators		TLMR 201 series 380 ml refill	LGWM 2/MR380
AGD series 125 ml	LAGD 125/WM2		

Technical data				
Designation	LGWM 2/(pack size)			
DIN 51825 code	KP2G-40	Water resistance		
NLGI consistency class	1–2	DIN 51 807/1, 3 hrs at 90 °C	1 max.	
Thickener	Complex calcium sulphonate	Oil separation		
Colour	Yellow	DIN 51 817,		
Base oil type	Synthetic (PAO)/ Mineral	7 days at 40 °C, static, %	3 max.	
Operating temperature range	–40 to +110 °C (–40 to +230 °F)	Lubrication ability R2F, running test B at 120 °C	Pass at 140 °C (285 °F)	
Dropping point DIN ISO 2176	>300 °C (>570 °F)	R2F, Cold chamber test (+20 °C) R2F, Cold chamber test (-30 °C)	Pass Pass	
Base oil viscosity 40 °C, mm ² /s	80	Copper corrosion DIN 51 811	2 max. at 100 °C (210 °F)	
100 °C, mm ² /s Penetration DIN ISO 2137 60 strokes, 10 ⁻¹ mm	8,6 280–310	Rolling bearing grease life ROF test L ₅₀ life at 10 000 r/min., hrs	1 824 ¹⁾ at 110 °C (230 °F)	
100 000 strokes, 10 ⁻¹ mm Mechanical stability Roll stability, 50 hrs at 80 °C. 10 ⁻¹ mm	+30 max.	EP performance Wear scar DIN 51350/5, 1 400 N, mm 4-ball test, welding load DIN 51350/4, N	1,5 max. ¹⁾ 4 000 min. ¹⁾	
Corrosion protection Emcor: – standard ISO 11007 – water washout test – salt water test (100% seawater)	0-0 0-0 0-0 0-01)	Fretting corrosion ASTM D4170 FAFNIR test at +25 °C, mg ASTM D4170 FAFNIR test at –20 °C, mg	5,2 ¹⁾ 1,1 ¹⁾	

Lubrication management

Just as asset management takes maintenance to a higher level, a lubrication management approach allows lubrication to be seen from a wider point of view. This approach helps to effectively increase machine reliability at a lower overall cost.



skf.com | mapro.skf.com | skf.com/lubrication

® SKF is a registered trademark of the SKF Group.

© SKF Group 2017

The contents of this publication are the copyright of the publisher and may not be reproduced (even extracts) unless prior written permission is granted. Every care has been taken to ensure the accuracy of the information contained in this publication but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of the use of the information contained herein.

PUB MP/P8 12056/2 EN · June 2017

Certain image(s) used under license from Shutterstock.com.